

ClearMatt – SpecData Sheet

Product Standards

Standard Gauges & Widths	
0.0157" x 49.212"	0.4mm x 1250mm
0.0200" x 48.5"	0.5mm x 1232mm
0.0250" x 48.5"	0.6mm x 1232mm
0.0320" x 48.0"	0.8mm x 1220mm
0.0400" x 48.0"	1.0mm x 1220mm
0.0500" x 48.0"	1.3mm x 1220mm
0.0630" x 48.0"	1.6mm x 1220mm
0.0800" x 48.0"	2.0mm x 1220mm
Additional gauges / widths available upon request. Minimum order quantities apply.	
Aluminum Standards	
Alloy:	5005
Material Finish:	Mill Finish
Temper:	H34
UTS:	20-26 KSI
UYS:	15 min KSI
Elongation:	3%
Bend Radii:	Gauge range specific – information available upon request.
Anodize Standards	
Gloss:	125, 250 Film = 50 Gloss 425, 750 Film = 30 Gloss
Optics:	N/A
Anodize Finish:	Etched
Film Min/Max:	0.000 – 0.999
Standard Film(s):	0.125, 0.250, 0.425, 0.750 mils
Color:	L = N/A A = N/A B = N/A
2 Sided Product:	No
UV Stable:	Yes
Ordering Specifics	
Available as Tolling:	Yes

Additional Product Information

Availability

Standard anodized lead time = two weeks.

Warranty

Warranties are job specific – please complete the Warranty Application Form available online at www.lorin.com.

Surface Protection

Lorin recommends but does not require that surface protection be applied to all bright sheet products.

Lorin Standards

Certification

- Chemical Composition – Standard
- Mechanical Composition – Standard
- Slit / Sheeted Certification – Upon Request

Packaging Standards

- Coil = Eye Vertical
- Sheet = Full Wooden Box

Shipping Quantity Tolerances

- +/- 10% Order Line Quantity