

## GoldBrite Ultra – SpecData Sheet

### Product Standards

Standard Gauges & Widths	
0.0200" x 48.5"	0.5mm x 1232mm
0.0250" x 48.5"	0.6mm x 1232mm
0.0300" x 48.0"	0.8mm x 1220mm
0.0400" x 48.0"	1.0mm x 1220mm
Additional gauges / widths available upon request. Minimum order quantities apply.	
Aluminum Standards	
<i>Alloy:</i>	C085
<i>Material Finish:</i>	Bright Mill Finish
<i>Temper:</i>	H18
<i>UTS:</i>	20 min
<i>UYS:</i>	17 min
<i>Elongation:</i>	1%
<i>Bend Radii:</i>	Gauge range specific – information available upon request.
Anodize Standards	
<i>Gloss:</i>	N/A
<i>Optics:</i>	N/A
<i>Anodize Finish:</i>	Brightened
<i>Film Min/Max:</i>	0.125-0.350
<i>Standard Film(s):</i>	0.150 mils 0.250 mils
<i>Color:</i>	L = 83.0 +/- 7.0 A = 0.0 +/- 2.0 B = 20.45 +/- 0.75
<i>2 Sided Product:</i>	No
<i>UV Stable:</i>	Yes
Ordering Specifics	
<i>Available as Tolling:</i>	Yes

### Additional Product Information

#### Availability

Standard anodized lead time = two weeks.

#### Warranty

Warranties are job specific – please complete the Warranty Application Form available online at [www.lorin.com](http://www.lorin.com).

#### Surface Protection

Lorin recommends but does not require that surface protection be applied to all bright sheet products.

### Lorin Standards

#### Certification

- Chemical Composition – Standard
- Mechanical Composition – Standard
- Slit / Sheeted Certification – Upon Request

#### Packaging Standards

- Coil = Eye Vertical
- Sheet = Full Wooden Box

#### Shipping Quantity Tolerances

- +/- 10% Order Line Quantity

### Other Classic Anodized Bright Gold Products

GoldBrite  
GoldBrite Ultra