



**CHAMPAGNE GOLD WITH A SATIN FINISH IS A PRODUCT DEVELOPED BY LORIN INDUSTRIES AND DESIGNED SPECIFICALLY FOR INTERIOR AND EXTERIOR APPLICATIONS.**

The Champagne Gold color is UV stable and will hold up well under direct sunlight exposure. If you are looking for an anodized aluminum product with a natural metallic beauty and a hint of gold, Lorin's Champagne Gold is the anodized finish for you.

## INDUSTRY DESIGNATIONS

**Aluminum Association**  
AA-M12-C21-A23  
**Mil A-8625F Classification**  
Type II Sulfuric Anodize

## INDUSTRY STANDARDS

**Mil A-8625F Anodizing Standard**  
Anodic coatings for aluminum and aluminum alloys

## ALUMINUM PROPERTIES

Alloy ..... 5005  
Temper ..... Half Hard  
Finish ..... Mill Finish

## MECHANICAL PROPERTIES

UTS ..... 20-26 ksi [138-179 MPa]  
YTS ..... 15 min [103 MPa]  
Elongation ..... 4% to 5% min

## CHEMICAL PROPERTIES

Si ..... 0.30 %  
Fe ..... 0.7 %  
Cu ..... 0.20 %  
Mn ..... 0.20 %  
Mg ..... 0.5 - 1.1 %  
Cr ..... 0.10 %  
Zn ..... 0.25 %  
Other ..... 0.15 %  
Al ..... Remainder

## ANODIZE FILM THICKNESS

Decorative Anodic layer:

## ANODIZE FINISH PROPERTIES

Optical ..... Not Applicable  
Gloss ..... Fine Matte, Satin Finish  
Color ..... Champagne Gold  
Color Target ..... < Δ Delta E of 6.0  
UV Stable ..... Yes  
Environment ..... Interior  
Quality Grade ..... 2  
Other ..... None

*This product is available for exterior use; a minimum film thickness of 0.250 mils (6 μm) is required.*

## WIDTH AVAILABILITY

48.0" (1219 mm)  
*Other widths can be custom ordered.*

## GAUGE AVAILABILITY

0.025" (0.6 mm)  
0.032" (0.8 mm)  
0.040" (1.0 mm)  
0.050" (1.3 mm)  
0.063" (1.6 mm)  
0.080" (2.0 mm)

## ANODIZED FINISH TEST DATA

CHARACTERISTIC	TEST METHOD	STANDARD	TEST RESULTS
Oxide Layer, Weight	ASTM B137 - Coating Dissolution		> 1.5 mg/cm <sup>2</sup> (9.7 mg/in <sup>2</sup> ) nominal
Film Hardness	ASTM D3363 - Pencil Hardness	Based on a anodic film thickness, 3.2 µm (0.125 mils)	4H Hardness
Seal Quality	ASTM B136 - Dye Stain	Dye Stain Test, No Stain Visible	Pass, No Visible Stain

### SECONDARY SERVICES

**Shearing, Width Capabilities:**

7" (178mm) - 62" (1575 mm)

**Shearing, Length Capabilities:**

Up to 192" (4876 mm)

**Shearing, Loading Gauge:**

Up to 0.080" (2.0 mm)

**Slitting, Width Capabilities:**

0.75" (19 mm) min

**Slitting, Loading Gauge:**

Up to 0.100" (2.5 mm)

**Other Secondary Services:**

Protective peel-able films

International packaging

Perforating and embossing

### MAINTENANCE AND CLEANING

The anodized aluminum finish can be washed with mild soap and water followed by a clean water rinse. For more information on cleaning anodized aluminum, please refer to the Aluminum Association Publication 92, Care of Aluminum or AAMA 609 & 610-09, Cleaning and maintenance guide for architecturally finished aluminum.

### SUSTAINABILITY AND LEED

**Recycled Content, 5005 alloy:**

100% recyclable

Recycled Content, 6.6%

Reclaimed-Virgin Material, 93.4%

2012.04.30 Mill#6

**Volatile Organic Compounds:**

The aluminum oxide layer does not contain any VOC's

### AVAILABILITY

The standard lead time for stocked gauges and widths is two weeks for anodizing and one week for any secondary services such as slitting, shearing and applying transparent protective films or paper.

Please check availability of Non-Stocked materials by contacting our sales staff using our toll free number 800.654.1159 or email your request to [info@lorin.com](mailto:info@lorin.com). Some raw materials may have extended lead times.

### TECHNICAL SUPPORT

A staff of factory trained personnel are available to offer technical assistance. Please call our toll free number 800.654.1159 or email your question to [info@lorin.com](mailto:info@lorin.com).

### PRODUCT SUPPORT PARTNERS

Lorin Industries works very closely with many manufacturers' in multiple markets who specialize in anodized aluminum fabrication. Our support staff can assist you if you are looking for finished components. Please call our toll free number 800.654.1159 or email your request for product and application support to [info@lorin.com](mailto:info@lorin.com).

### WARRANTY

A limited warranty is available upon request. The warranty is issued on a per project basis and can be applied for on line by completing an application for warranty at [Lorin.com](http://Lorin.com).